

STANDARD SALES SPECIFICATIONS FOR ELTEX[®] MED PH22D630

| Property | Unit | Test Method | Specification Range |
|-----------------------------------|-------------------|--|---------------------|
| Melt Flow Rate (190 °C - 2.16 kg) | g/10min | ISO 1133-1 | 0.25 - 0.36 |
| Density | kg/m ³ | ISO1183-1 or ISO1183-2 conditioning ISO 17855-2 | 920.0 - 924.0 |
| Melting Point | °C | INEOS method | 109 - 113 |
| Odor | - | INEOS method | Max 2 |
| Colour | - | INEOS method | Max 2 |
| Pellet Contamination | - | INEOS method | Max 0 |

Date of issue: January 2024

Valid until: January 2025

When the validity period expires, please ensure that you download the latest version from our website.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

Siege Social: INEOS Services Belgium SA, rue de Ransbeek 310, B-1120 Neder-over-Heembeek. TVA BE 0871 521 046 RPM Bruxelles.
Citibank NA Bruxelles 570-1281855-58.