

22D730

Product Technical Information

LDPE for Blown film

22D730 is an autoclave, low density polyethylene grade for film application. 22D730 is developed to give an extra strong film for heavy duty film applications such as sacks and pallet shrink.

Applications

22D730 is intended for applications such as

- Heavy duty bags
- Shrink films
- Liners
- Construction and agricultural films

Properties		Test Method	Value	Units
Physical				
Melt flow rate (190°C/2.16 kg)		ISO 1133	0.3	g/10 min
Density		ISO 1183	922	kg/m ³
Melting temperature		ISO 11357/03	110	°C
Vicat softening temperature		ISO 306	96	°C
Additive free				
Film*				
Tensile strength	MD/TD	ISO 1184	25/23	MPa
Tensile strain @ break	MD/TD	ISO 1184	400/600	%
Tensile modulus	MD/TD	ISO 1184	170/180	MPa
Coefficient of friction	Dynamic	ISO 8295	> 0.5	-
Dart drop		ASTM D 1709	450	g
Haze		ASTM D1003	15	%
Gloss (45°)		ASTM D2457	43	%

- Data should not be used for specification work

* Film properties are measured on a 125µm film sample produced on a 60mm W&H extruder with IBC cooling at BUR=2.5. MD = machine direction, TD = transverse direction



22D730

Storage and Handling

22D730 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation which results in odour generation and colour changes, and can have negative effects on the physical properties of the product.

Processing guidelines

22D730 is easily processed on conventional extruders.

Recommended melt temperature range is from 170°C to 200°C. Due to differences in screw a die head designs the optimum temperature adjustments are individual and should be sought for each production line.

With suitable equipment 22D730 can be drawn down to 70-75 micron.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com.

Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.