



# Eltex<sup>®</sup> A4009MFN1325

## Product Technical Information

Eltex<sup>®</sup> A4009MFN1325 is a high density polyethylene. It is a homopolymer with a narrow molecular weight distribution primarily intended for the extrusion of monofilaments.

## Applications

- Extrusion of monofilaments
- High tenacity tapes
- Cereal liners film
- Injection moulding
- Blow-moulding for food packaging

## Benefits and Features

- High tenacity monofilaments and tapes
- Very low gel content
- Superior processability & surface quality
- Very low MVTR (Moisture Vapour Transmission Rate)

Properties		Test Method	Value	Units
<b>Physical</b>				
Density @ 23°C		ISO 1183/A	960	kg/
Melt Flow Rate	190°C/2.16 kg	ISO 1133	0.9	g/10
Melt Flow Rate	190°C/5 kg	ISO 1133	2.8	g/10mi
Melt Flow Rate	190°C/21.6 kg	ISO 1133	36	g/10min
Apparent dynamic viscosity @ 190°C and 100 s <sup>-1</sup>		-	1700	Pa.s
<b>Thermal</b>				
Melting point (DSC – 2 <sup>nd</sup> heating)		ISO 11357-3	136	°C

- The values given are typical values measured on the product. These values should not be considered as specifications



# Eltex<sup>®</sup> A4009MFN1325

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

## Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to [psnohreg@ineos.com](mailto:psnohreg@ineos.com). Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

## Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website [www.ineospolyolefins.com](http://www.ineospolyolefins.com). Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

## Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.