



BPD4720UA

Product Technical Information

BPD4720UA is a natural high density polyethylene grade designed for the extrusion of jackets for power cables.

Benefits & Features

BPD4720UA offers a unique balance of properties combining the following features:

- Excellent extrudability
- Outstanding stress-cracking resistance
- Good toughness and resistance to heat deformation
- Good abrasion resistance
- Low shrinkage
- UV stabilized

Applications

BPD4720UA is well-suited to the extrusion of colorable jackets for power cables.

BPD4720UA is formulated with an antioxidant and UV stabilizers package that delivers excellent ageing properties.

We recommend that you consult your INEOS technical representative for further advice on the use of **BPD4720UA**.

Specifications

BPD4720UA meets the following raw material specifications:

- ISO1872 – PE KHN 45 D-006
- ASTM D 1248 – type III, Class A, Category 4, Grade E10, J5

Compliance to Regulations

When adequately processed with relevant additive package, **BPD4720UA** will allow producing a jacket meeting the following industry cable specifications:

- IEC 60502-2, Class ST7

BPD4720UA

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190°C/5.0 kg	ISO 1133-1	2.0	g/10min
Melt Flow Rate	190°C/ 2.16 kg	ISO 1133-1	0.60	g/10 min
Physical				
Density	23°C, conditioning	ISO 17855-1	945	kg/m ³
Mechanical				
Vicat Softening Temperature	Method A50 (10N, 50°C/h)	ISO 306	119	°C
Shore D hardness	1 second	ISO 868	66	-
Shore D hardness	3 seconds	ISO 868	61	-
Shore D hardness	15 seconds	ISO 868	59	-
Tensile Modulus	23°C, 1 mm/min	ISO 527-1,-2	1000	MPa
Tensile Strength at Break	23°C, 50 mm/min	ISO 527-1,-2	27	MPa
Tensile Strength at Yield	23°C, 50 mm/min	ISO 527-1,-2	22	MPa
Elongation at Break	23°C, 50 mm/min	ISO 527-1,-2	700	%
Retention of mechanical properties after ageing	in oven 10days at 100°C	IEC 60811-401	>75	%
Environment				
Environmental Stress Cracking Resistance (BTT)	F ₀ , 50°C, 10% Igepal	ASTM D1693	> 1000	h
Environmental stress cracking resistance (FNCT)	2% Arkopal N100, 4 MPa, 80°C	ISO 16770	> 40	h
Electrical				
Volume resistivity	50 Hz	ASTM D257	> 10 ¹³	Ω.m
Dielectric constant	1 MHz, 23°C	ASTM D150	2.6	-
Data should not be used for specification work				

Processing guidelines

The good processing characteristics of **BPD4720UA** allow wide latitude of both equipment and process conditions. It is recommended to set an extrusion temperature profile resulting in a melt temperature in the range of 210 - 230°C. Processing above 230°C should be avoided to prevent heat degradation.

BPD4720UA in its original packaging is ready for use. Extreme temperature changes and a high percentage of atmospheric humidity can lead to condensation within the packaging. Pre-drying of the material is advisable in this case.

On a commercial line 150mm - 20 L/D a typical temperature profile would be:

- Barrel: 180 - 190 - 200 - 200 °C
- Head: 210 °C
- Die: 210°C



BPD4720UA

Storage

BPD4720UA should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website www.ineos.com where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website www.ineos.com. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

November, 2023

Published by

INEOS Olefins & Polymers Europe