

# LL6910LA

## Product Technical Information

LLDPE film products

## Benefits & Features

LL6910LA is a linear low density polyethylene copolymer containing hexene-1 as the co-monomer which offers the following properties:

- Very low gel level
- Good optical properties
- High temperature resistance
- High creep resistance
- Excellent sealability and hot-tack strength

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

## Applications

LL6910LA is rigid blown film grade offering a certified low level of gels making it ideal for lamination or thin film applications with highly decorative printing.

Properties	Conditions	Test Methods	Values	Units
<b>Rheological</b>				
Melt Flow Rate		ISO 1133-1	1	g/10min
<b>Physical</b>				
Density		ISO 1183-2	936	kg/m <sup>3</sup>
<b>Mechanical</b>				
1% Secant modulus		ISO 527-3	450	MPa
Dart drop impact	Method A	ASTM D1709	65	g
Elmendorf tear strength	MD/TD	ASTM D1922	35/325	gf/25 μm
Elongation at break	MD/TD	ISO 527-3	780/990	%
Tensile stress at break	MD/TD	ISO 527	54/36	MPa
Tensile stress at yield	MD/TD	ISO 527	18/21	MPa
<b>Optical</b>				
Gloss	45°	ASTM D2457	50	GU
Haze		ASTM D1003	13	%

**Data should not be used for specification work**

(\*) - 38μm film. 2:1 blowup ratio, 225°Cmelt temperature – MD = Machine direction TD = Transverse direction



# LL6910LA

## Extrusion conditions

LL6910LA can be processed on most standard extrusion equipment. Optimisation may be required depending on the exact end use requirements. Recommended melt temperature range is 180 – 230°C.

## Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

---

### Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website [www.ineos.com](http://www.ineos.com) where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

### Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website [www.ineos.com](http://www.ineos.com). Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

### Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.