

M29N430

Product Technical Information

Ethylene-MethAcrylic-Acid-Copolymer (EMAA) for extrusion coating.

Benefits & Features

M29N430 is an additive free ethylene-methacrylic-acid-copolymer (EMAA) with 9,3% MAA content. Its special polymer structure gives the following properties:

- Improved adhesion properties to polar substrates, especially with aluminium foil and metallised film and robust adhesion resistance for demanding filling goods
- Excellent processability in mono- and coextrusion at high line speed and/or low coating weights
- Exhibits good sealing properties enhanced by the presence of the comonomer

Applications

M29N430 is a specialty extrusion coating resin with improved adhesion characteristics. Main application fields include aluminium foil and metallized film coating both for industrial use, food and flexible packaging.

We recommend that you consult your INEOS technical representative for further advice on the use of **M29N430**.

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190 °C/2.16Kg	ISO 1133-1	8.0	g/10 min
Co-monomer				
Methacrylic Acid Content		INEOS Test Method	9.3	%
Mechanical*				
Shore hardness D		ISO 868	48	-
Tensile Modulus	23 °C, 1 mm/min	ISO 527-2	162	MPa
Tensile strength at Break	23 °C, 50 mm/min	ISO 527-2	21.4	MPa
Tensile strain at Break	23 °C, 50 mm/min	ISO 527-2	515	%
Flexural Modulus		ISO 178	150	MPa
Izod Impact Strength		ISO 180	55.9	kJ/m ²
Thermal				
DSC Melting Temperature	10 °C/min	ISO 11357-3	100	°C
Vicat Softening Temperature	10 N	ISO 306/A50	77	°C

Data should not be used for specification work

* Measurements made on compression moulded plaques

Processing guidelines

M29N430 can be processed on commercial extrusion coating equipment over the melt temperature range from 260 to 290°C. Low coating weights can be obtained at extrusion rates normally used for common substrates.

Identical extrusion and processing parameters should be used as for conventional LDPE of identical MFR.

When extruding **M29N430**, precautions should be taken to prevent equipment corrosion.

The extrusion equipment has to be designed for acid copolymers to avoid corrosion.

July 2021

Published by

INEOS Olefins & Polymers Europe



M29N430

The resin should not be left standing in the extruder for extended periods.
After extrusion of **M29N430** the extruder should be purged with LDPE.

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C.
Exposure to direct sunlight should be avoided as this may lead to product deterioration.
It is advised to process the product within maximum one year after delivery.

Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website www.ineos.com where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website www.ineos.com. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

July 2021

Published by
INEOS Olefins & Polymers Europe