



Eltex[®] PF6612AA

Product Technical Information

Eltex[®] PF6612AA is a metallocene LLDPE grade produced in Europe.

Benefits & Features

Eltex[®] PF6612AA is a polyethylene copolymer containing hexene-1 as the comonomer produced with a metallocene catalyst. It offers the following properties:

- High impact strength and rigidity
- Excellent optical properties
- Very good bubble stability and extrudability
- Low temperature sealing characteristics

Applications

Eltex[®] PF6612AA has been developed for use in collation shrinkwrap, food packaging and other thin film applications where an excellent balance between film strength and rigidity is required together with good optical properties. In addition, Eltex[®] PF6612AA offers easy extrudability.

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

Properties	Conditions	Test Methods	Values	Units
Rheological				
Melt Flow Rate	190°C/2.16Kg	ISO 1133-1	1.3	g/10min
Physical				
Density ISO 1872-1	23°C	ISO 1183-2	926	kg/m ³
Mechanical*				
Dart drop impact	Method A	ASTM D 1709	200	g
Tensile strength at Yield	MD/TD**	ISO 527-3	13 / 13	MPa
Tensile strength at break	MD/TD**	ISO 527-3	55 / 50	MPa
Tensile strain at break	MD/TD**	ISO 527-3	570 / 690	%
1% Secant modulus	MD/TD**	ISO 527-3	230 / 270	MPa
Elmendorf tear strength	MD/TD**	ASTM D 1922	160 / 560	g/25 µm
Optical*				
Haze		ASTM D 1003	7	%
Gloss	45°	ASTM D 2457	65	% ₀₀
Thermal				
Peak DSC melting temperature	2nd heating	ASTM D 3418	120	°C
Additives				
Antioxidants				

Data should not be used for specification work

* 25 µm film 2.5:1 blow-up ratio, 220°C melt temperature - MD = machine direction, TD = transverse direction



Eltex[®] PF6612AA

Processing guidelines

Eltex[®] PF6612AA in lean blends can be processed on most standard extrusion equipment. Optimisation of conditions may be necessary, depending on the exact blend used.

Eltex[®] PF6612AA rich film formulations are often processed on modified LDPE machinery, but for the best performance the use of purposely designed LLDPE machinery is recommended. Particular attention should be paid to maintaining a low melt temperature, and an efficient bubble cooling system should be employed. The recommended melt temperature range is 190 - 230°C.

Storage

The product should be stored in a dry and dust free environment at temperature below 50°C. Exposure to direct sunlight should be avoided as this may lead to product deterioration. It is advised to process the product within maximum one year after delivery.

Regulatory Information

The product and uses described herein may be subject to specific requirements or limitations for use in certain applications like food contact, drinking water or medical devices. Further information may be obtained from the website www.ineos.com where a specific Regulatory Certificate is available for each grade under the heading "SDS & Regulatory Certificate".

Unless specifically indicated, the product mentioned herein is not suitable for applications in the medical or pharmaceutical sectors.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Safety Data Sheet (SDS) that may be obtained from the website www.ineos.com. Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.