

# H19G-01

POLYPROPYLENE HOMOPOLYMER

## TECHNICAL DATASHEET

### Product Description

H19G-01 is a polypropylene homopolymer designed for the extrusion of continuous filament yarn, continuous bulked filament yarn and staple fiber. Its benefits include consistent processing, color stability, and excellent spinning characteristics. H19G-01 meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.<sup>1</sup>

### Typical Properties<sup>2</sup>

Property	English Units	SI Units	ASTM Method
<b>Resin Properties</b>			
Density		0.910 g/cc	D792
Melt Flow Rate (230°C/2.16 kg)		19 g/10 min	D1238
<b>Injection Molded Specimen Test</b>			
Tensile Strength (2 in/min) @ Yield	5,400 psi	37 MPa	D638
Elongation (2 in/min) @ Yield	8.9 %	8.9 %	D638
Flexural Modulus, 1% Secant	258,000 psi	1,780 MPa	D790A
Notched Izod Impact Strength @ 23°C	0.5 ft-lb/in	2.8 kJ/m <sup>2</sup>	D256
Hardness, Rockwell R	105	105	D785
HDT @ 66 psi (455 kPa)	226 °F	109 °C	D648
Gloss Units, 60° Angle	95	95	D2457

<sup>1</sup>Consult the Regulatory Position Statement for specific use conditions and limitations.

<sup>2</sup>Typical property values will vary and are not to be used as specification limits.

## Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, please refer to the Regulatory Position Statement (RPS) online at [www.ineos-op.com](http://www.ineos-op.com), or call + 1-800-527-5419.

## Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Safety Data Sheet (SDS) contains the available product health and safety information for this material and can be found at [www.ineos-op.com](http://www.ineos-op.com). Before using any material, a customer is advised to consult the SDS for the product under consideration for use.

The Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS O&P is altered or modified, different shipping descriptions may apply and the SDS of the original material should not be used.

All information contained herein, whether technical or otherwise, is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranties, express or implied, are made with respect to the accuracy, reliability, or completeness of this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA will not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information will not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name and logo INEOS are trademarks of the INEOS Group and its affiliated companies and businesses.